

Rec'd PCT/PTO 15 JUN 2005

PCT/IB 03 / 05734
05.12.03



Europäisches
Patentamt

European
Patent Office

Office européen
des brevets

10/539101

REC'D 13 DEC 2003
WIPO PCT

Bescheinigung

Certificate

Attestation

Die angehefteten Unterla-
gen stimmen mit der
ursprünglich eingereichten
Fassung der auf dem näch-
sten Blatt bezeichneten
europäischen Patentanmel-
dung überein.

The attached documents
are exact copies of the
European patent application
described on the following
page, as originally filed.

Les documents fixés à
cette attestation sont
conformes à la version
initialement déposée de
la demande de brevet
européen spécifiée à la
page suivante.

Patentanmeldung Nr. Patent application No. Demande de brevet n°

03103338.4

PRIORITY DOCUMENT
SUBMITTED OR TRANSMITTED IN
COMPLIANCE WITH
RULE 17.1(a) OR (b)

Der Präsident des Europäischen Patentamts:
Im Auftrag

For the President of the European Patent Office

Le Président de l'Office européen des brevets
p.o.

R C van Dijk



Anmeldung Nr:
Application no.: 03103338.4
Demande no:

Anmeldetag:
Date of filing: 10.09.03
Date de dépôt:

Anmelder/Applicant(s)/Demandeur(s):

Koninklijke Philips Electronics N.V.
Groenewoudseweg 1
5621 BA Eindhoven
PAYS-BAS

Bezeichnung der Erfindung/Title of the invention/Titre de l'invention:
(Falls die Bezeichnung der Erfindung nicht angegeben ist, siehe Beschreibung.
If no title is shown please refer to the description.
Si aucun titre n'est indiqué se referer à la description.)

Electric device with phase change material and method of manufacturing the same

In Anspruch genommene Priorität(en) / Priority(ies) claimed / Priorité(s)
revendiquée(s)
Staat/Tag/Aktenzeichen/State/Date/File no./Pays/Date/Numéro de dépôt:

Internationale Patentklassifikation/International Patent Classification/
Classification internationale des brevets:

G11C/

Am Anmeldetag benannte Vertragsstaaten/Contracting states designated at date of
filing/Etats contractants désignées lors du dépôt:

AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HU IE IT LU MC NL
PT RO SE SI SK TR LI

Electric device with phase change material and method of manufacturing the same

The invention relates to an electric device with a body having a resistor comprising a phase change material being changeable between a first phase and a second phase, the resistor having a first electrical resistance when the phase change material is in the first phase, and a second electrical resistance different from the first electrical resistance
5 when the phase change material is in the second phase.

The invention further relates to a method of manufacturing such an electric device.

10 US-5,933,365 discloses an embodiment of an electric device having a resistor comprising a phase change material, which is able to be in a first, e.g. crystalline, phase and a second, e.g. amorphous, phase. The resistor with the phase change material in the first phase and the resistor with the phase change material in the second phase have different values of the electrical resistance. One or both of the first phase and the second phase may be partly
15 amorphous and partly crystalline. In the remainder the terms "crystalline" and "amorphous" are used to refer to a crystalline phase or a mainly crystalline phase, and to an amorphous phase or a mainly amorphous phase, respectively.

The resistor is electrically connected to a first conductor and a second conductor such that the value of the electrical resistance can be measured. The resistor, the
20 first conductor and the second conductor are able to conduct a current which via heating enables transitions of the phase change material between the first phase and the second phase. It is believed that for a transition from a phase with a relatively good conductivity such as a crystalline phase or a mainly crystalline phase, to a phase with a relatively poor conductivity such as an amorphous phase or a mainly amorphous phase, the heating by a sufficiently
25 strong current melts the phase change material. The heating ends when switching off the current. The phase change material then cools down and arranges in a more amorphous order.

When inducing a transition from a phase with a relatively low electrical conductivity to a phase with a relatively high electrical conductivity, the heating is initially counteracted by the poor conductivity, which limits the current conducted through the phase

change material. It is believed that by applying a sufficiently high voltage, i.e. a voltage higher than the so called threshold voltage, across the resistor it is possible to locally induce an electrical breakdown in the phase change material, which leads to a high local current density. The corresponding heating is then sufficient to increase the temperature of the phase change material above its crystallization temperature thereby enabling the phase transition from the amorphous phase to the crystalline phase.

The known electric device is an electrically writable and erasable memory cell, which carries information encrypted in the value of the electrical resistance. The memory cell is assigned, e.g., a "0" when the resistance is relatively low and a "1" when the resistance is relatively high. The resistance may be easily measured by supplying a voltage across the resistor and measuring the corresponding current. The memory element is written and erased by inducing a transition from a first phase to a second phase as described above.

It is a disadvantage of the known electric device that the electric device deteriorates when repeatedly switched between the first phase and the second phase, i.e. the lifetime, also called the life span or referred to as the endurance, of the electric device is limited.

It is an object of the invention to provide an electric device as described in the opening paragraph, which has a relatively good endurance.

The invention is defined by the independent claims. The dependent claims define advantageous embodiments.

According to the invention this object is realized in that the phase change material constitutes a conductive path between a first contact area and a second contact area, a cross section of the conductive path being smaller than the first contact area and the second contact area. Here, the term "contact area" defines the area in which the phase change material is electrically connected to an electrical conductor such as the first conductor or the second conductor, which is composed of a material other than the phase change material. In the known device the phase change material is located in an aperture. The contact area and the cross section of the conductive path are both equal to the cross section of the aperture, i.e. the contact area is equal to the cross section of the conductive path. In the known device the phase change occurs in a volume of the phase change material, which comprises this contact area. At the interface, i.e. at this contact area, repetitive phase changes and the corresponding high current densities cause a deterioration of the material, which leads to a deterioration of

the electric device, in particular when the phase change material comprises relatively reactive atoms such as Te. In the electric device according to the invention, the minimum cross section of the conductive path is well inside the phase change material and not, like in the known electric device, identical to the contact area. The current density is then highest inside the phase change material and therefore, the Joule heating is more effective inside the phase change material. This reduces the interactions between the phase change material and the other materials at the interface, i.e. at the first contact area and/or the second contact area, leading to an improved endurance.

In an embodiment a part of the conductive path having the cross section constitutes a volume of phase change material, the volume having an electrical resistance which is larger than an electrical contact resistance at the first contact area and/or at the second contact area, independent whether the phase change material is in the first phase or the second phase. In such an electric device the Joule heating at the first contact area and/or at the second contact area are each smaller than the Joule heating inside the volume of the phase change material where the current density is high. This further reduces the interactions between the phase change material and the other materials at the first contact area and/or the second contact area, leading to an improved endurance. An additional advantage is that the electrical power is dissipated, i.e. converted to heat, mainly at the location where the phase change occurs. By reducing the dissipation at positions where the phase change does not occur the total electrical power required for inducing a phase transition is reduced.

Preferably, the electrical resistance of the volume is larger than the electrical contact resistance at both the first contact area and the second contact area, independent whether the phase change material is in the first phase or the second phase. In this case, it is assured that the phase change occurs in the volume, which is inside the phase change material.

Preferably, the contact resistance at the first contact area and at the second contact area are smaller than $10^{-7} \text{ V cm}^2/\text{A}$ because then the dissipation at the first contact area and at the second contact area is relatively small.

In an embodiment the electric device further comprises a heating element able to conduct an electrical current for promoting a phase transition by Joule heating. The heating by the heating element allows for a more efficient use of the electrical energy when inducing a phase transition. It is then advantageous if the heating element is arranged in parallel to the resistor. An electrical device with a heating element arranged in parallel to the resistor is described in the European Patent Application by the same applicant "Electric device with

phase change material and parallel heater", which is submitted at the same date as the present application. It is incorporated by reference in this application in its entirety. In this case the endurance of the electric device is further increased because the switching no longer requires an electrical breakdown induced by a voltage larger than the threshold voltage. In the electric device according to this embodiment the Joule heating by the heating element is effective even when the phase change material is in the amorphous phase because the heating element is arranged in parallel to the resistor. When the phase change material is in the amorphous phase, a voltage applied to the resistor leads to a current flowing at least partly through the heating element, thereby leading to an effective heating of the phase change material without requiring an electrical breakdown. This heating is promoting the phase change thereby improving the endurance of the electric device.

In an embodiment the heating element has a heating element electrical resistance R_H which is smaller than the first electrical resistance and the second electrical resistance, i.e. which is in particular smaller than the electrical resistance $R_{R,A}$ of the resistor with the phase change material in the amorphous phase. As a consequence the current mainly flows through the heating element when the phase change material is in the amorphous phase. It is advantageous if the heating element electrical resistance R_H is a factor of ten or more smaller than the electrical resistance $R_{R,A}$. When inducing the phase transition is controlled by the current through the electric device the following holds: the smaller the heating element electrical resistance R_H with respect to the electrical resistance $R_{R,A}$ the higher is the current flowing through the heating element and the higher the corresponding Joule heating. When inducing the phase transition is controlled by the voltage over the resistor the parallel heating element has the advantage that a lower voltage can be used. The smaller the heating element electrical resistance R_H with respect to the electrical resistance $R_{R,A}$ the smaller is the voltage required over the heating element and the resistor. At a lower voltage the Joule heating required for inducing the phase change is then achieved by a higher current through the heating element. This has particular advantages when the electric device is integrated in an advanced IC process in which the voltage is relatively low. At the same time the electric current through the phase change material is reduced thereby reducing electro-migration in the phase change material, thus leading to an improved endurance.

In the embodiment described in the previous paragraph a phase transition is induced without an electrical break down in the phase change material. Repeatedly switching a phase change material by an electrical breakdown deteriorates the electric device, in particular for phase change materials comprising relative reactive atoms such as e.g. Te.

Therefore, an electric device according to this embodiment of the invention, in which the electric breakdown is avoided, has an improved endurance.

Another disadvantage associated with switching by electrical breakdown is that the electrical breakdown is a statistical process. Thus the value of the breakdown voltage is a statistical parameter as well, which may depend on temperature and the time elapsed since the last switching. In order to assure reliable switching, a voltage well above the average threshold voltage has to be applied in the known electric device. However, the voltages available with CMOS devices are scaling down when scaling down the dimensions of the CMOS device. Thus, future electric devices should be reliably operated at relatively low voltages. In the electric device according to this embodiment of the invention the electric breakdown is not required and a voltage below the threshold voltage is sufficient to induce a phase transition.

A preferred lower limit of the heating element electrical resistance R_H is that it is larger than 0.3 times the minimum of the first electrical resistance and the second electrical resistance, i.e. larger than 0.3 times the electrical resistance $R_{R,C}$ of the resistor with the phase change material in the crystalline phase. An electric device fulfilling this condition has the advantage that the change of the resistance is reliably measurable.

When the resistor and the heating element are connected in parallel, the total electrical resistance R_T of these two elements is given by $R_T = R_R * R_H / (R_R + R_H)$. The electrical resistance R_R of the resistor depends on the phase of the phase change material whereas the heating element electrical resistance R_H is independent of the phase of the phase change material. In the limit that the heating element electrical resistance R_H is much smaller than the electrical resistance $R_{R,A}$, the total electrical resistance $R_{T,A}$ with the phase change material in the amorphous phase is approximately equal to R_H .

Defining a scaling factor k by $R_H = k * R_{R,C}$ the total electrical resistance $R_{T,C}$ with the phase change material in the crystalline phase is $R_{T,C} = R_{R,C} * k / (k + 1)$. The change of the total resistance is $\Delta R_T = R_{T,A} - R_{T,C} \approx R_H - R_{T,C} = (k - k / (k + 1)) * R_{R,C} = R_{R,C} * k^2 / (k + 1)$. Within this approximation the relative change of the total resistance is $\Delta R_T / R_{T,C} = k$. The smaller the relative change of the total resistance, the more difficult it is to reliably measure it. A smaller relative change of the total resistance typically requires a more sophisticated detection circuit and/or a longer measurement time. The inventors have established that a relative change of 0.3, i.e. of 30 %, or more is relatively easy measurable in a relatively short time.

Preferably, the scaling factor k should be between 1 and 4, i.e. $1 \leq k \leq 4$ because then the detection of the change of the total resistance ΔR_T is relatively robust while at the same time the Joule heating by the heating element is relatively effective.

It is advantageous if the heating element and the resistor are in direct contact because the Joule heating by the heating element is then particularly effective. For the same reason it is advantageous if the heating element is in direct contact with the volume of the phase change material having a cross section smaller than the first contact area and the second contact area.

In an embodiment the heating element is composed of a heating element material which is of a composition $X_{100-(t+s)}Si_sY_t$ where t and s denote atomic percentages satisfying $t < 0.7$ and $s+t > 0.3$, and X comprises one or more elements selected from Ti and Ta, and Y comprises one or more elements selected from C and N. Preferably, X is substantially free from Ti because Ta is less reactive with the phase change material than Ti. Preferably, s is smaller than or equal to 0.7 because otherwise the conductivity of the parallel heater is relatively low which requires a relatively large parallel heater. When the phase change material comprises Ge, mixing of Ge and Si is reduced when s is smaller than or equal to 0.7. It is further advantageous if Y comprises N because the heating element material usually has a polycrystalline structure which is stabilized by the presence of the nitrogen atoms, i.e. the polycrystalline structure is changed to a relatively small extent when heating the phase change material.

In an embodiment the resistor constitutes a memory element, and the body comprises an array of memory cells, each memory cell comprising a respective memory element and a respective selection device, and grid of selection lines, each memory cell being individually accessible via the respective selection lines connected to the respective selection device. The selection device may comprise a bipolar transistor or a diode such as, e.g. a pn diode. Such an electric device is a random access memory (RAM) device, which is suited as a non-volatile memory device.

In a preferred variation of this embodiment the selection device comprises a metal oxide semiconductor field effect transistor (MOSFET) having a source region, a drain region and a gate region, and the grid of selection lines comprises N first selection lines, M second selection lines, N and M being integers, and an output line, the resistor of each memory element electrically connecting a first region selected from the source region and the drain region of the corresponding metal oxide semiconductor field effect transistor to the output line, a second region of the corresponding metal oxide semiconductor field effect

transistor selected from the source region and the drain region and being free from the first region, being electrically connected to one of the N first selection lines, the gate region being electrically connected to one of the M second selection lines. In such a memory device the memory elements are selected by a MOSFET, which allows for relatively high operating speed and relatively low operating voltage.

The method of manufacturing an electric device according to the invention comprises the steps of providing a main surface of a pre-fabricated electric device with a layer of the phase change material, and reducing a cross section of a conductive path in the layer between a first contact area and a second contact area, the cross section being smaller than the first contact area and the second contact area. In a manufacturing process it is more convenient to first form a layer of the phase change material by, e.g., a layer deposition and to subsequently change its shape such that the cross section is reduced instead of directly forming a layer having the required small cross section. According to the invention the step of reducing the cross section may be executed before the layer of the phase change material is contacted at the first contact area and/or the second contact area.

In an embodiment of the method the main surface has a step profile and the step of reducing the cross section comprises an anisotropic etching step for forming a sidewall spacer along at least a part of the step profile. The cross section is then the cross section of the sidewall spacer and it is determined by the thickness of the layer of the phase change material and by the height of the step profile. The step profile may be obtained, e.g., by depositing a layer of an e.g. dielectric material, which is subsequently patterned by e.g. lithography. In this case the height of the step profile is identical to the thickness of the layer of the dielectric material. Thus it is possible to obtain a layer of the phase change material, which has a cross section, which is entirely determined by the thickness of these two layers, i.e. independent of e.g. the minimum dimension obtainable by lithography. The dimensions of the cross section are typically below 20 nm times 20 nm. Preferably, they are below 10 nm times 10 nm.

These and other aspects of the electric device according to the invention will be further elucidated and described with reference to the drawings, in which:

Fig. 1 is a top view of an embodiment of the electric device at a first stage of the manufacturing,

Fig. 2 is a cross section of the pre-fabricated electric device of Fig. 1 along line II-II,

Fig. 3 is a top view of the pre-fabricated electric device at a second stage of the manufacturing,

Fig. 4 is a cross section of the pre-fabricated electric device of Fig. 3 along line IV-IV,

Fig. 5 is a top view of the pre-fabricated electric device at a third stage of the manufacturing,

Fig. 6 is a cross section of the pre-fabricated electric device at a fourth stage along line VI-VI of Fig. 5,

Figs. 7 and 8 are top views of the other embodiment of the pre-fabricated electric device at a fifth stage and a sixth stage of the manufacturing, respectively, and

Fig. 9 is a plot of the crystallization speed as function of the Sb/Te ratio.

The Figures are not drawn to scale.

The electric device 100, shown in Figs. 1-8 at various stages of the manufacturing, has a body 102, which comprises a substrate 101 which may comprise, e.g., a single crystal p-doped silicon semiconductor wafer. In the body 102 a resistor 107 is embedded in a dielectric 123 and 126, e.g. silicon oxide. The resistor 107 is composed of a phase change material being changeable between a first phase and a second phase. The resistor 107 has a first electrical resistance when the phase change material is in the first phase, and a second electrical resistance different from the first electrical resistance when the phase change material is in the second phase.

In one embodiment the phase change material is a composition of formula $Sb_{1-c}M_c$ with c satisfying $0.05 \leq c \leq 0.61$, and M being one or more elements selected from the group of Ge, In, Ag, Ga, Te, Zn and Sn. An electric device with a phase change material of this composition is described in the non-pre-published European Patent Application with application number 03100583.8 attorney's docket number PHNL030259, the priority of which is claimed by this application and which is incorporated herein by reference in its entirety. Preferably, c satisfies $0.05 \leq c \leq 0.5$. Even more preferably, c satisfies $0.10 \leq c \leq 0.5$. A group of advantageous phase change materials has one or more elements M other than Ge and Ga at concentrations which are in total smaller than 25 atomic percent and/or comprise in total less than 30 atomic percent of Ge and/or Ga. Phase change materials

comprising more than 20 atomic percent of Ge and Ga and one or more elements selected from In and Sn at concentrations which are in total between 5 and 20 atomic percent have a relatively high crystallization speed and at the same time a relatively high stability of the amorphous phase.

5 In an embodiment the phase change material is a composition of formula $Sb_aTe_bX_{100-(a+b)}$ with a, b and $100-(a+b)$ denoting atomic percentages satisfying $1 \leq a/b \leq 8$ and $4 \leq 100-(a+b) \leq 22$, and X being one or more elements selected from Ge, In, Ag, Ga and Zn. The phase change material may be, e.g., $Sb_{72}Te_{20}Ge_8$.

10 In yet another embodiment the phase change material is a composition of formula $(Te_aGe_bSb_{100-(a+b)})_cTM_{100-c}$ where the subscripts are in atomic percentages, a is below 70 percent, b is above 5 percent and below 50 percent, c is between 90 and 99.99 percent, and TM denotes one or more transition metal elements. Alternatively, the transition metal is omitted and the phase change material is a composition of formula $Te_aGe_bSb_{100-(a+b)}$ where the subscripts are in atomic percentages, a is below 70 percent and b is above 5 percent and
15 below 50 percent such as, e.g., $Ge_2Sb_2Te_5$. Other examples of the phase change material are $Te_{81}Ge_{15}S_2As_2$ and $Te_{81}Ge_{15}S_2Sb_2$.

The phase change material may be deposited by sputtering as described in the article "Phase-change media for high-numerical-aperture and blue-wavelength recording" by H.J. Borg et al., Japanese Journal of Applied Physics, volume 40, pages 1592-1597, 2001.

20 The resistor 107 constitutes a memory element 170, and the body 102 comprises an array of memory cells, each memory cell comprising a respective memory element 170 and a respective selection device 171. In the embodiment shown in Figs. 1-8 the electric device 100 has a 3x3 array but the invention is not limited to an array of this size or to an array of this shape. The body 102 further comprises a grid of selection lines 120, 121
25 such that each memory cell is individually accessible via the respective selection lines 120, 121 connected to the respective selection device 171.

In the embodiment shown in Figs. 1-8 the selection device 171 comprises a ~~metal~~ oxide semiconductor field effect transistor (MOSFET), and more specifically an NMOS transistor. The MOSFET has n-doped source regions 172, n-doped drain regions 173,
30 and gate regions 174. The source regions 172 and the drain regions 173 may comprise more than one portion of n-doped material, such as a lightly doped n-portion and a more heavily doped n+ portion. The n-doped source region 172 and the drain region 173 are separated by a channel region. The gate regions 174, formed above the channel region, control the flow of current from the source region 172 to the drain region 173 through the channel region. The

gate region 174, preferably comprises a layer of polycrystalline silicon. The gate region 174 is separated from the channel region by a gate dielectric layer.

The grid of selection lines 120, 121 comprises $N=3$ first selection lines 120 and $M=3$ second selection lines 121, and an output line. The resistor 107 of each memory element 170 electrically connects a first region selected from the source region 172 and the drain region 173 of the corresponding MOSFET to the output line. A second region of the corresponding MOSFET selected from the source region 172 and the drain region 173 and being free from the first region, is electrically connected to one of the N first selection lines 120. The gate region 174 is electrically connected to one of the M second selection lines 121. In the embodiment shown in Figs. 2-9 the first region is the source region 172 and the second region is the drain region 173. In another embodiment not shown the first region is the drain region 173 and the second region is the source region 172. The selection lines 120, 121 are connected to line selection devices and row selection devices, respectively. These latter selection devices are not shown.

The gate region 174 and the drain region 173 are provided with layers of tungsten silicide and tungsten plugs 122 for electrically connecting the gate region 174 and the drain region 173 to the selection lines 121 and 120, respectively. The selection lines 120 and 121 are formed from a conductive material such as, e.g., aluminum or copper. The source region 172 is provided with a layer of tungsten silicide and a tungsten plug as well.

In a process of manufacturing the electric device 100, first the array of selection devices 171 and the grid of selection lines 120, 121 are formed, e.g. using standard IC technology. One terminal of each selection device 171, in the embodiment of Figs. 1-8 the source region 172, is provided with an electrical conductor 124 such as, e.g., a tungsten plug. The selection device 171, the selection lines 120, 121 and the electrical conductor 124 are mutually insulated from each other by and embedded in a dielectric material 123, e.g., silicon dioxide such that the electrical conductor 124 is exposed as shown in Figs. 1 and 2. Preferably, the surface comprising the exposed electrical conductor 124 is polished by chemical mechanical polishing (CMP) for obtaining a relatively smooth and relatively plain surface.

In a subsequent step this surface is provided with a layer 109 of a dielectric material such as, e.g., silicon nitride or silicon carbide. In the layer 109 openings 108 are formed by means of, e.g., lithography such that the electrical conductors 124 and parts of the dielectric 123 adjacent to the electrical conductors 124 are exposed as shown in Fig. 4. The main surface of the pre-fabricated electric device 100 thus obtained has a step profile.

Subsequently, the main surface, i.e. the layer 109 and the openings 108 of pre-fabricated electric device 100, is provided with a layer 107 of phase change material as shown in Fig. 5. The thickness LT of layer 107 which is typically 5-50 nm, preferably approximately 15 nm, determines the width of the minimal cross section of the phase change material as will be described below. In one embodiment a layer 110 of a conductive material such as, e.g., TiN is deposited onto the layer 107. Layer 110 is used to reduce the electrical resistance between the electrical conductor 124 and the part of layer 107 undergoing the phase change. In another embodiment, not shown, layer 110 is omitted.

Onto layer 107 or, if present onto layer 110, masks 111 and 112 are formed by, e.g., lithography or electron beam writing. Masks 111 each cover parts of layer 107 and layer 110, if present, which cover the respective electric conductors 124. Masks 112 cover other parts of layer 107 and layer 110, if present, onto which further electrical conductors 125 will be formed later on. For every memory element, masks 111 and 112 are separated by a distance L which is typically below 300 nm and preferably between 20 and 200 nm. When lithography is used to form the mask 111 and the mask 112, the minimum distance L is preferably approximately equal to the minimum dimension achievable by the lithography. The shorter the distance L the smaller the electrical power required to induce a phase transition between the first and the second phase. The distance L determines the length of the phase change material which will have a cross section smaller than the phase change material at the electrical conductors 124 as will be described below. The phase change material having the reduced cross section is referred to as the volume of the phase change material.

If present the parts of layer 110 not covered by masks 111 and 112 are removed by isotropic etching using, e.g., a solution comprising HF. The result obtained at this stage of the process of manufacturing the electric device 100 is shown in Fig. 4. Note that due to the isotropic etching an under etch occurs, see Figs. 4 and 5. Then the parts of layer 107 not covered by masks 111 and 112 are anisotropically etched, using, e.g., a reactive ion etch comprising Cl. As a result side wall spacers composed of the phase change material are formed inside the openings 108 at the position not covered by masks 111 and 112. This implies reducing a cross section of a conductive path in the layer 107 between the first contact area covered by mask 111, and a second contact area covered by mask 112. The cross section is smaller than the first contact area and the second contact area. For each memory element 170 the side wall spacers formed by layer 107 are electrically connected to those parts of layer 107 and layer 110, if present, which were covered by masks 111 and 112 during the etching step. As shown in the cross section of Fig. 6 the side wall spacers formed

of layer 107 have a width W that is substantially equal to the thickness LT of layer 107. In other words, the main surface has a step profile formed by layer 109 and the step of reducing the cross section comprises an anisotropic etching step for forming a side wall spacer along at least a part of the step profile.

5 After removing the masks 111 and 112 the pre-fabricated electric device 100 shown in top view in Fig. 5 is obtained. Every memory cell of this electric device 100 has a layer 107 of phase change material, which comprises a part defined by mask 111, and a part defined by mask 112. These two parts are connected by two side wall spacers formed of layer 107.

10 In an embodiment the method further comprises a step of covering the prefabricated electric device 100 shown in Fig. 5 by a layer 106 of a heating element material for forming a heating element 106 able to conduct a current for enabling a transition from the first phase to the second phase. The layer 106 is composed of a heating element material with a melting point higher than that of the phase change material. The melting point of the
15 heating element material is preferably at least 100 degrees Celsius, more preferably at least 250 degrees Celsius higher than that of the phase change material. Preferably, the heating element material does not react with the phase change material. Preferably, the resistivity of the heating element material is in the range of 0.1 to 10 cm mV/A. When the phase change material is selected from the class of $Te_aGe_bSb_{100-(a+b)}$ where the subscripts are in atomic
20 percentages, a is below 70 percent and b is above 5 percent and below 50 percent, the phase change material has a resistivity of 1 to 4 cm mV/A, e.g. 2 cm mV/A, and the resistivity of the heating element material is preferably between 0.5 and 20 cm mV/A. When the phase change material is selected from the class of $Sb_{1-c}M_c$ with c satisfying $0.05 \leq c \leq 0.61$, and M being one or more elements selected from the group of Ge, In, Ag, Ga, Te, Zn and Sn, the
25 phase change material has a resistivity of approximately 0.2 to 0.8 cm mV/A and the resistivity of the heating element material is preferably between 0.1 and 4 cm mV/A.

In an embodiment the heating element material is of a composition $X_{100-(t+s)}Si_tY_s$ where t and s denote atomic percentages satisfying $t < 0.7$ and $s + t > 0.3$, and X comprises one or more elements selected from Ti and Ta, and Y comprises one or more
30 elements selected from C and N. Preferably, X is substantially free from Ti because Ta is less reactive with the phase change material than Ti. Preferably, s is smaller than or equal to 0.7 because otherwise the conductivity of the parallel heater is relatively low which requires a relatively large parallel heater. When the phase change material comprises Ge, mixing of Ge and Si are reduced when s is smaller than or equal to 0.7. It is further advantageous if Y

comprises N because the heating element material usually has a polycrystalline structure which is stabilized by the nitrogen atoms, i.e. the polycrystalline structure is changed to a relatively small extent when heating the phase change material. Examples of this class of heating element material are TaSiN, Ta₂₀Si₄₀N₄₀, TiSiN or Ta₂₀Si₄₀C₄₀. Alternatively, the heating element material may be composed of TiN, TaSi₂, TaN_x where x satisfies 0.3 < x < 0.7, TiAlN, TiC, TiWC or, e.g. p, doped polycrystalline silicon.

After providing the layer 106 of the heating element material masks 111' and 112' are formed which masks are similar to the masks 111 and 112. Subsequently, the layer 106 is anisotropically etched using, e.g., a plasma etch comprising CF₄ : CHF₃. As shown in the cross section of Fig. 6 side wall spacers are formed of layer 106 in a way analogous to the formation of the side wall spacers of layer 107. The side wall spacers formed of layer 106 have a width V that is substantially equal to the thickness of layer 106.

In an alternative embodiment layer 107 and layer 106 are interchanged, i.e. layer 106 is provided before providing layer 107 on top of layer 106. In another embodiment layer 106 is separated from layer 107 by an intermediate layer which may comprise, e.g., silicon dioxide. Also in this embodiment the heating element 106 is parallel to the resistor 107. In contrast to the embodiment described before, in this embodiment the resistor 107 is not in direct contact with the heating element 106.

In an alternative embodiment both layer 107 and layer 106 are provided prior to forming the masks 111 and 112. Both layer 107 and layer 106 are then anisotropically etched without the need of an additional step of forming the masks 111' and 112'.

In one embodiment the method of manufacturing the electric device 100 comprises a step in which a mask 128 is provided having openings 129 such that for each of the memory cells one of the two side wall spacers formed of layer 107 is exposed while the other of the two side wall spacers formed of layer 107 is covered by mask 128 as shown in Fig. 7. In a subsequent step this mask is then used to remove, e.g. by etching, the exposed portions of layer 106 and layer 107. As a result in every memory cell these two parts are now connected by only one side wall spacer formed of layer 107. Subsequently, mask 128 is removed. In another embodiment the mask 128 is omitted and the layer 106 and the layer 107 each have two side wall spacers.

The pre-fabricated electric device 100 is provided with a dielectric layer 126 of, e.g., silicon dioxide. In one embodiment the prefabricated electric device shown in Fig. 7 is then subjected to a material removal treatment, such as, e.g., chemical mechanical polishing, to reduce the height of the side wall spacers of layers 106 and 107 and to obtain a

smooth surface which is advantageous for further processing. It is then advantageous if layer 109 is composed of two layers of different materials, e.g. a lower layer of a relatively hard material such as, e.g., silicon nitride on top of which is a layer of a relatively soft material such as, e.g., silicon oxide. During the material removal treatment the relatively hard layer is
5 used as a stopping layer thereby yielding a side wall spacer of layer 107 of a well defined height H of preferably 10 to 100 nm. After this material removal treatment, surface 199, shown in Fig. 7, is obtained. The layer 107 thus obtained, i.e. having one or two side walls, forms the resistor 170 of the electric device 100.

Subsequently, an additional dielectric layer 126' is provided in which
10 dielectric layer 126' openings 132, shown in Fig. 8, are created to expose for each memory cell a part of the layer 106, if present, the conductive layer 110, if present, or layer 107 which was covered by mask 112 at an earlier stage. These openings 132 are provided with further electric conductors for electrically contacting the resistor 170. In a later step the further electric conductor is electrically connected to the output line.

15 The electric device 100 thus obtained has a body 102, which has a resistor 170. The resistor 170 is composed of a layer 107 of a phase change material being changeable between a first phase and a second phase. The resistor 170 has a first electrical resistance when the phase change material is in the first phase, and a second electrical resistance different from the first electrical resistance when the phase change material is in
20 the second phase. The body 102 further has a heating element formed by layer 106. The heating element is able to conduct a current for enabling a transition from the first phase to the second phase. The heating element is arranged in parallel to the resistor.

The phase change material constitutes a conductive path between a first contact area and a second contact area. When layer 110 is omitted, the first contact area is the
25 area in which the electrical conductor 124 contacts the layer 107 of the phase change material, see e.g. Figs. 1 and 4, and the second contact area is the area in which the further electrical conductor provided to opening 132 contacts the layer 107 of the phase change material, see Fig. 8. A cross section of the conductive path constituted by the layer of the phase change material is smaller than the first contact area and the second contact area. When
30 layer 110 is present, the first contact area and the second contact area are effectively the areas in which the current moves from layer 110 into layer 107. Due to the isotropic etching of layer 110 and the anisotropic etching of layer 107, the layers 110 do not contact the side wall spacers of layer 107 directly, but at a distance, see Figs. 4 and 5. In this case, the first contact

area and the second contact area are still not at the border of the volume defined by the side wall spacer and are larger than a cross section of the side wall spacer.

The current density inside the side wall spacer is higher than at the first contact area and at the second contact area and therefore, the phase change material at the side wall spacer rather than at the first contact area and/or at the second contact area will undergo a phase transition.

In an embodiment layer 110 is omitted and the volume of the phase change material with the reduced cross section has a length L of 50 nm, a height H of 20 nm and a width W of 15 nm. The cross section is thus H times W which equals 300 nm^2 . The first contact area defined by electrical conductor 124 is equal to the second contact area defined by opening 132 is equal to 100 nm times 100 nm . Thus the first contact area and the second contact area each have a size of 10000 nm^2 which is larger than the cross section of 300 nm^2 . The phase change material is $\text{Sb}_{72}\text{Te}_{20}\text{Ge}_8$. The volume of the resistor with the reduced cross section has a resistance of 800 Ohm when the phase change material is in the crystalline phase and of more than 100 kOhm when the phase change material is in the amorphous phase. The electrical conductor 124 and the further electrical conductor are composed of tungsten. The contact resistance in the first contact area and the second contact area are each 100 Ohm. Thus, the contact resistance at the first contact area and the second contact area are each smaller than the resistance of the volume of the phase change material having the reduced cross section.

The electric device 100 is particularly advantageous when the phase change material is a fast growth material with a crystallization speed of 1 m/s or more. This type of phase change materials which comprise compositions of formula $\text{Sb}_{1-c}\text{M}_c$ with c satisfying $0.05 \leq c \leq 0.61$, and M being one or more elements selected from the group of Ge, In, Ag, Ga, Te, Zn and Sn, have a crystallization speed v_{cr} which is approximately a linear function of the ratio Sb/M , see e.g. Fig. 9 for the case M comprising Te. For a given desired switching time t which may be imposed by the bandwidth of the selection device 171, the length L and the composition of the phase change material are adjusted such that $L/(2t) \approx v_{cr}$ holds. Here, the factor 2 accounts for the fact that the crystallization starts from the two outer ends of the volume of the phase change material having the reduced cross section.

In an alternative embodiment of the method of manufacturing the electronic device 100 the layer 109 is omitted. The layer 107 of phase change material is directly provided to the prefabricated electric device 100 shown in Fig. 1. Subsequently a resist layer is provided which is sensitive to electrons. Into this resist layer a pattern is written with an

electron beam. The pattern defines at least the volume of the phase change material. In one embodiment the electron beam also write the pattern defined in the previous embodiments by masks 111 and 112. In an alternative embodiment masks 111 and 112 are formed by photo lithography analogous to the embodiments described above and the electron beam is solely
5 used to write the pattern defining the volume of the phase change material having the reduced cross section. This latter embodiment has the advantage that the throughput is relatively high because the electron beam has to be used only for defining a relatively small part of the pattern. Subsequently, the resist is developed and the further electric device is further processed analogous to the embodiments described above.

10 In summary, the electric device 100 has a body 102 having a resistor 107 comprising a phase change material being changeable between a first phase and a second phase. The resistor 107 has a first electrical resistance when the phase change material is in the first phase, and a second electrical resistance different from the first electrical resistance when the phase change material is in the second phase. The phase change material constitutes
15 a conductive path between a first contact area and a second contact area. A cross section of the conductive path is smaller than the first contact area and the second contact area. The body 102 may further have a heating element 106 able to conduct a current for enabling a transition from the first phase to the second phase. The heating element 106 is preferably arranged in parallel to the resistor 107.

20 It should be noted that the above-mentioned embodiments illustrate rather than limit the invention, and that those skilled in the art will be able to design many alternative embodiments without departing from the scope of the appended claims. In the claims, any reference signs placed between parentheses shall not be construed as limiting the claim. The word "comprising" does not exclude the presence of other elements or steps than those listed
25 in a claim. The word "a" or "an" preceding an element does not exclude the presence of a plurality of such elements.

CLAIMS:

1. An electric device (100) with a body (102) having a resistor (107) comprising a phase change material being changeable between a first phase and a second phase, the resistor (107) having a first electrical resistance when the phase change material is in the first phase, and a second electrical resistance different from the first electrical resistance when the phase change material is in the second phase, the phase change material constituting a conductive path between a first contact area and a second contact area, a cross section of the conductive path being smaller than the first contact area and the second contact area.
2. An electric device (100) as claimed in Claim 1, wherein a part of the conductive path having the cross section constitutes a volume of phase change material, the volume having an electrical resistance which is larger than an electrical contact resistance at the first contact area and/or at the second contact area, independent whether the phase change material is in the first phase or the second phase.
3. An electric device (100) as claimed in Claim 1, further comprising a heating element (106) able to conduct an electric current for enabling a transition from the first phase to the second phase.
4. An electric device (100) as claimed in Claim 3, wherein the heating element (106) is arranged in parallel to the resistor (107).
5. An electric device (100) as claimed in Claim 4, wherein the heating element (106) has a heating element electrical resistance which is smaller than the first electrical resistance and the second electrical resistance.
6. An electric device (100) as claimed in Claim 5, wherein the heating element electrical resistance is larger than 0.3 times the minimum of the first electrical resistance and the second electrical resistance.

7. An electric device (100) as claimed in Claim 3, wherein the heating element (106) is in direct contact with the resistor (107).

8. An electric device (100) as claimed in Claim 1, wherein the resistor (107) constitutes a memory element (170), and the body (102) comprises:

- an array of memory cells, each memory cell comprising a respective memory element (170) and a respective selection device (171), and
 - a grid of selection lines (120, 121),
- each memory cell being individually accessible via the respective selection lines (120, 121) connected to the respective selection device (171).

9. An electric device (100) as claimed in Claim 8, wherein:

- the selection device (171) comprises a metal oxide semiconductor field effect transistor having a source region (172), a drain region (173) and a gate region (174), and
 - the grid of selection lines (120, 121) comprises N first selection lines (120), M second selection lines (121), and an output line,
- the resistor (107) of each memory element (170) electrically connecting a first region selected from the source region (172) and the drain region (173) of the corresponding metal oxide semiconductor field effect transistor to the output line, a second region of the corresponding metal oxide semiconductor field effect transistor selected from the source region (172) and the drain region (173) and being free from the first region, being electrically connected to one of the N first selection lines (120), the gate region (174) being electrically connected to one of the M second selection lines (121).

10. Method of manufacturing an electric device (100) as claimed in Claim 1, comprising the steps of:

- providing a main surface of a pre-fabricated electric device (100) with a layer (107) of the phase change material, and
- reducing a cross section of a conductive path in the layer (107) between a first contact area and a second contact area, the cross section being smaller than the first contact area and the second contact area.

11. A method as claimed in Claim 10, wherein the main surface has a step profile and the step of reducing the cross section comprises an anisotropic etching step for forming a side wall spacer along at least a part of the step profile.

5 12. A method as claimed in Claim 10, wherein a part of the conductive path having the cross section constitutes a volume of phase change material, and the step of reducing the cross section comprises the sub-steps of:

- providing a resist layer sensitive to electrons,
- writing a pattern with an electron beam into the resist layer, the pattern
- 10 defining at least the volume of the phase change material, and
- developing the resist.

ABSTRACT:

The electric device (100) has a body (102) having a resistor (107) comprising a phase change material being changeable between a first phase and a second phase. The resistor (107) has a first electrical resistance when the phase change material is in the first phase, and a second electrical resistance different from the first electrical resistance when the phase change material is in the second phase. The phase change material constitutes a conductive path between a first contact area and a second contact area. A cross section of the conductive path is smaller than the first contact area and the second contact area. The body (102) may further have a heating element 106 being able to conduct a current for enabling a transition from the first phase to the second phase. The heating element (106) is preferably arranged in parallel to the resistor (107).

Fig. 1




FIG. 1

2/7




FIG. 2





FIG. 4






FIG. 5

5/7




FIG. 6





FIG. 9






FIG. 8

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

☐ BLACK BORDERS

☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES

☐ FADED TEXT OR DRAWING

☒ BLURRED OR ILLEGIBLE TEXT OR DRAWING

☐ SKEWED/SLANTED IMAGES

☐ COLOR OR BLACK AND WHITE PHOTOGRAPHS

☐ GRAY SCALE DOCUMENTS

☐ LINES OR MARKS ON ORIGINAL DOCUMENT

☐ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY

☐ OTHER: _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.